



## AIR-Z®

The structured mat from RHEINZINK

RHEINZINK offers its own structured mat for RHEINZINK-standing seam roof systems, copings and inlay gutters. AIR-Z is a three-dimensional mat made of nylon filament installed over underlayment with substrates of plywood or Oriented Strand Board (OSB). AIR-Z was engineered for sloped roof applications starting from 5/8:12 pitch. AIR-Z compensates for structural tolerances up to 2 mm.

**For sloped roofs from 5/8:12**

**Creates a thermal break between metal roof and sheathing**

**Reduces roof noise from rain or sleet**

**Retains strength and rigidity**

**Easy to cut and can be installed vertically or horizontally**

### Benefits of AIR-Z

RHEINZINK AIR-Z provides a number of benefits for metal roofing. The main purpose is to provide an open air space to allow moisture to flow away or evaporate. Another advantage is the thermal break created between the metal roofing and sheathing resulting in a reduction of energy use. AIR-Z also assists in the reduction of noise from driving rain and sleet.

### Experience through Invention

Choosing a RHEINZINK roof represents a decision for longevity and quality. RHEINZINK is considered to be the inventor of the structured mat for roofing applications. It was developed by our Engineers over 20 years ago as the sustainable and dependable method to provide an air space so that moisture is not trapped against the backside of the zinc.



Fig. 1: Typical standing seam application

### Working with AIR-Z

AIR-Z is UV resistant for up to 6 months and retains its strength and rigidity in temperatures ranging from -100 degrees F to +250 degrees F. AIR-Z needs to be installed in temperatures 23 degrees F and greater. Due to its flexibility, AIR-Z is easy to cut and install – simply roll out over approved underlayment. AIR-Z can be placed horizontally or vertically.

Technical information and system details available upon request. To learn more about AIR-Z and other RHEINZINK products, please visit [www.rheinzink.us](http://www.rheinzink.us)

### Technical Data

Physical Properties	Property	Imperial Units	Metric Units	Test Method
	<b>Material:</b>	Nylon 6		
	<b>Thickness:</b>	.31 in	8 mm	ASTM D5199
	<b>Weight</b>	6.2 oz/yd <sup>2</sup>	210.2 g/m <sup>2</sup>	ASTM D5261
	<b>UV Stability</b>	>85% residual tensile strength		ASTM D5035 <sup>1</sup>
	<b>Low Temperature:</b>	-100 degrees F	-73 degrees C	
	<b>High Temperature:</b>	+250 degrees F	+121 degrees C	
	<b>Fuel/Gasoline Submersion:</b>	Stable		
	<b>Tensile Strength:</b>	>114 lbs/ft longitudinal direction >74 lbs/ft transversal direction	MD ≈ 1.7 kN/m longitudinal direction CD ≈ 1.1 kN/m transversal direction	ASTM D5035 <sup>1</sup>
	<b>pH Range:</b>	3 to 12		
	<b>Fire Rating:</b>	NFPA class A UBC class I		ASTM E84
	<b>Flame Spread:</b>	0		ASTM E84-11a
	<b>Smoke Density:</b>	30		ASTM E84-11a
Packaging	Property	Imperial Units	Metric Units	
	<b>Width:</b>	39.3 in.	99.82 cm	
	<b>Length:</b>	246 feet	75 m	
	<b>Area:</b>	89.7 yd <sup>2</sup>	75 m <sup>2</sup>	
	<b>Area:</b>	807.3 ft <sup>2</sup>	75 m <sup>2</sup>	
	<b>Roll Diameter:</b>	33.5 in.	85.09 cm	
	<b>Gross (Roll) Weight:</b>	35.9 lbs	16.28 kg	

<sup>1</sup> Modified